

Technical Data Sheet



Injection Mortar FIS V Zero

Prepared on: 20.04.2021
Version: 1.0

Reviewed on: -

Printing Date: 07.10.2021
Page: 1 von 1

Product Description: injection mortar, labelling free
Colour: grey

Technical Data:

Product Data	Testing Method	Results
--------------	----------------	---------

Stability		
UV-resistance (sunlight)		resistant
Temperature resistance		120 °C
Water resistance		resistant
Water absorption		after 14 days: 0.8 %
Cleaning agents		1 % tenside solution no effects
Long-term behaviour (Freezing and thawing resistance)	EOTA part 5	approved suitability for outside applications

Physical properties		
Shrinkage		< 0.8 %
Hardness Shore A	ISO 868	after 60 min: > 80
Density		1.6 - 1.8 g/cm ³
pH		after 24 h: 7 - 8 (22 °C)

Workability features		
Viscosity (20 °C)	Brookfield (Sp.7) 10 rpm	200 – 300 Pas
Open time (15 – 20 °C)		5min
Curing time (21 °C)		60 min
Shelf life		12 months